



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C02F 1/42, B01J 20/02, 20/10	A1	(11) International Publication Number: WO 96/09985 (43) International Publication Date: 4 April 1996 (04.04.96)
---	----	---

<p>(21) International Application Number: PCT/US95/12327</p> <p>(22) International Filing Date: 26 September 1995 (26.09.95)</p> <p>(30) Priority Data: 08/313,349 27 September 1994 (27.09.94) US</p> <p>(71) Applicant: SYRACUSE UNIVERSITY [US/US]; 113 Bowne Hall, Syracuse, NY 13244-1200 (US).</p> <p>(72) Inventors: TAVLARIDES, Lawrence, L.; 5117 Muirfield Drive, Fayetteville, NY 13066 (US). DEORKAR, Nandu; 101 Smith Lane #22, Syracuse, NY 13210 (US).</p> <p>(74) Agents: GOLDMAN, Michael, L. et al.; Nixon, Hargrave, Devans & Doyle LLP, Clinton Square, P.O. Box 1051, Rochester, NY 14603 (US).</p>	<p>(81) Designated States: CA, JP, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).</p> <p>Published <i>With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i></p>
--	--

(54) Title: CHEMICALLY ACTIVE CERAMIC COMPOSITIONS WITH A THIOL AND/OR AMINE MOIETY

(57) Abstract

Composite materials useful for removing metal ions from solutions such as aqueous waste streams comprise an inorganic ceramic support such as silica gel that has active hydroxyl groups. The support is reacted with a silane linking compound or with a titanizing agent. A chelating compound, which can be a thiol or an amine, is attached to the silane or to titanium atoms of the titanized surface of the support.

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgystan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LJ	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Larvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

- 1 -

**CHEMICALLY ACTIVE CERAMIC COMPOSITIONS
WITH A THIOL AND/OR AMINE MOIETY**

FIELD OF INVENTION

5

The present invention relates to novel chemically active ceramic compositions and their preparation and use for removing metal ions from solutions, especially aqueous waste streams.

10

BACKGROUND OF THE INVENTION

Many industries utilize heavy metals and/or rare earth metals in their manufacturing processes. Such use typically results in liquid (generally aqueous) waste streams that contain residues of the rare earth or heavy metals utilized in the given manufacturing process. For example, the waste streams resulting from electronics, electroplating, and photographic processes typically contain metal ions such as copper, nickel, zinc, chromium (III), chromium (VI), cadmium, aluminum, lead, antimony, silver and gold, amongst others in various aqueous solutions such as sulfates, chlorides, fluoroborates and cyanides. Because of the potential adverse effect of such substances on health and the environment, the removal of rare earth metals and heavy metal ions from aqueous waste streams is a problem of continuing significance.

For the purposes of the present invention, heavy metals will be defined generally as elements having atomic numbers greater than 20, as defined by the Periodic Chart of the Elements and are metallic at ambient conditions. Rare earth metals are defined as those heavy metals having atomic numbers 57 through 71 inclusive. Actinides are those heavy metals having atomic numbers greater than 89. For example, aluminum, arsenic, antimony, copper, nickel, zinc, chromium, cadmium, mercury, platinum, palladium and gold are all heavy

- 2 -

metals typically found in the waste stream of common manufacturing processes. In addition, cesium and strontium (and other radioactive metals) are found in aqueous waste streams in the nuclear industry.

5 The conventional and predominant method of treatment of the waste streams described above is the precipitation of the metal ions in the form of hydroxides or carbonates. That method of removing heavy metals is largely undesirable because it results in a sludge that is difficult
10 and/or expensive to remove and separate from the waste stream. Furthermore, the recovered sludge is typically deposited in a hazardous waste site, raising additional environmental concerns. Finally, it is difficult to separate the individual metal from the resultant sludge for
15 recycling back into the manufacturing process. Other recovery methods include evaporation, reverse osmosis, ion exchange, electrolytic metal recovery, and solvent extraction. These methods, however, have varying levels of success and do not typically allow for the quick and
20 inexpensive separation and removal of the individual metals from the waste streams.

 Another common technique for the separation and recovery of rare earths is solvent extraction. However, the main difficulty in a solvent extraction recovery process
25 arises from the low concentration at which these metal ions exist in the aqueous stream generated from hydrometallurgical processes. Also, the identical complexing behavior of all the rare earths due to their similar ionic sizes and chemistry limits the ability to
30 separate out the individual rare earth metals from the sample collected in the solvent extraction process. See Nakamura, Tachimori and Sato, 15 Journal of Nuclear Science and Technology, 829-834 (1978).

 A more recent method of removing metals from waste
35 streams features using compositions which include chelating

- 3 -

agents that are bound to inorganic carriers. Chelating agents, also known as multidented ligands, are compounds which are capable of complexing with various metal ions in solution where one chelation molecule has the capacity to attach a metal ion at two or more positions. Those chelating agents are molecules which contain one or more of the same donor atom (e.g., "electron sufficient" atoms such as oxygen, nitrogen, sulfur etc.) or two or more different donor atoms through which coordinate and/or covalent bonds are formed between the metal ion and chelating agent. One such composition is disclosed in United States Patent No. 3,886,080 to Schucker et al. ("Schucker"). Schucker discloses a composition in which a chelating agent has been rendered immobile or insoluble by chemically coupling a chelating agent, selected from a defined group of chelates, by bonding the chelating agent to a silane coupling agent using a diazo linkage. The silane coupling agent, in turn, is bonded to the inorganic carrier.

The compositions defined by Schucker have many disadvantages. Initially, the method of making the compositions disclosed by Schucker inherently limits the types of compounds that can be utilized in the composition. For example, the only chelating agents that can be used are those compounds having an unsaturated ring structure. Furthermore, because the chelate and the silane coupling agent are bound by a diazo linkage, it is obvious that only compounds capable of forming such a linkage can be used to produce the composition. Furthermore, the Schucker process for making the compositions is a five step process. The large number of steps required can result in decreased capacities (i.e., the amount of metal the composition is capable of chelating) due to the aggregate inefficiency of the chemical reactions utilized to produce a given composition. Lastly, the Schucker compositions are not capable of separating individual metals and, therefore, are

- 4 -

not useful in metal recovery processes which seek to recycle individual metals back into the manufacturing process from which they came. Accordingly, there exists a need for more cost efficient processes for the separation and removal of heavy metal and/or rare earth metals from waste streams by producing compositions having a variety of chelating agents which are specific and selective toward desired metal ions.


SUMMARY OF THE INVENTION

10

The present invention relates to chemically active ceramic compositions for separating heavy metal ions from solutions, especially aqueous waste streams. More particularly, the present invention relates to novel compositions that have very high capacities for chelating heavy and/or rare earth metals and can be readily designed to selectively remove individual metals. Furthermore, the present invention relates to methods of making and using those compositions.

20


One embodiment of the present invention comprises a composite material having the formula:




25

wherein at least one of R_1 - R_3 is SUPPORT-O- and other of R_1 - R_3 are the same or different and are unsubstituted or halosubstituted alkyl groups having 1-5 carbon atoms and R_4

30 is




35




5 In the formula above, a is an integer from 1-20, b is an integer from 2-8, c is an integer from 0-5, and d is an integer from 1-5.

A second embodiment of the present invention comprises a composite material which contains the compounds
 10 of the following formulae:



15

and



20

wherein

at least one of R₄₁-R₄₃ and one of R_{41'}-R_{43'} are

SUPPORT-O-

25

R₄₄ is $\text{---}(\text{CH}_2)_a\{\text{S---}(\text{CH}_2)_b\}_c\text{SH}$,

R_{44'} is an amine; and


other of R₄₁-R₄₃ and R_{41'}-R_{43'} are the same or different and are unsubstituted or halo-substituted alkyl groups having 1-5 carbon atoms, R₄₄ or R_{44'}.

30

A third embodiment of the present invention comprises a composition having the formula:

35

- 6 -




5

wherein

1) at least one of R_9 , R_{10} or R_{11} is SUPPORT-O- and R_{12} is

10




15

wherein:

a) R_{13} is


i) an unsubstituted or lower aryl or lower alkyl substituted saturated hydrocarbon chain having 1-20 carbon atoms,

20




wherein R_{17} - R_{20} are the same or different and are -H or $-(CH_2)_fCH_3$, where f is an integer of 0-20 and e is an integer of 1-5, or

25



wherein R_{21} is $\text{---} (\text{CH}_2)_m \text{CH}_3$,


5



and g is 1-10, h is 1-10, j is 1-20, k is 1-5, m is 0-10 and X^- is a chlorine, bromine or iodine ion;

b) two or three of R_{14} , R_{15} and R_{16} are

10 $\text{---} (\text{CH}_2)_m \text{CH}_3$,




and other of R_{14} , R_{15} and R_{16} are H; and

15

2) other of R_9 , R_{10} , and R_{11} are R_{12} , or unsubstituted or halo-substituted alkyl groups having from 1 to 5 carbon atoms.

A fourth embodiment of the present invention comprises a composite material having the formula:

20



25 wherein one or both of R_7 and R_8 is SUPPORT-O- and the other of R_5 , R_6 , R_7 and R_8 are the same or different and are monoamines or polyamines, wherein a nitrogen is bonded to said Ti atom.

The invention also includes a method of removing heavy metal ions from a liquid stream, such as an aqueous waste stream, comprising the step of contacting the stream with a composite material of the present invention under conditions effective to complex heavy metal ions onto the composite material.

BRIEF DESCRIPTION OF THE DRAWINGS

10 FIG. 1 is a flow chart of the process for separation and recovery of heavy metal ions with chemically active ceramic compositions.

FIG. 2 is a flow chart illustrating the process of the invention by using different inventive compositions in a series of multiple adsorbent beds for metal ion separation and/or metal recovery.

20 FIG. 3 illustrates the relationship between the ratio of cadmium ion concentration in an effluent stream to the cadmium ion concentration in a feed stream versus the bed volumes passed through a column of a composition prepared according to the present invention.

FIG. 4 illustrates the relationship between the cadmium ion concentration in an effluent stream versus the bed volumes of a strip solution passed through a column of a composition prepared according to the present invention which is initially loaded with a known amount of cadmium.

30 FIG. 5 illustrates the ratio of the respective zinc, cadmium and lead ion concentrations in an effluent stream to the respective zinc, cadmium and lead ion concentrations in a feed stream versus the bed volumes passed through a column of composite materials prepared according to the present invention.


DETAILED DESCRIPTION OF THE INVENTION

The present invention relates to novel compositions that have very high capacities for chelating heavy and/or rare earth metals and can be readily designed to selectively remove individual metals. Furthermore, the present invention relates to methods of making those compositions and of using them for removing metal ions from solutions and, especially, from aqueous waste streams.



10 The ceramic inorganic carriers useful to prepare the compositions of the present invention are those ceramic materials having terminal hydroxy groups. For example, alumina, titanium oxide, zirconium oxide, and silica-alumina are all useful in the compositions of the present invention. 15 Silica gels are preferred due to the high density of hydroxy groups per unit surface area, higher overall surface area, and varying particle size. The silica gels preferred for use in the present compositions are in the form of particles (e.g., beads) having a diameter generally in the range of 3 20 mesh (about 0.635 cm) to 270 mesh (about 53 μm), Tyler Sieve scale. Most preferably, the silica gel beads used in accordance with the present invention have a diameter in the range of 14 to 270 mesh, have surface area of about 350 to 600 m^2/gm and pore sizes (diameters) of about 40 to 150 25 angstroms. For the purposes of the present invention, the inorganic carrier portion of the inventive composite materials shall hereafter be designated "SUPPORT". According to the present invention, chemical compounds used as linking groups (i.e., groups which attach the chelating 30 agent to the support) provide a linking chain between the chelating agent and the support to effect covalent bonding. This linkage is achieved by covalently bonding one end of the linking group to the support and another end of the linking group to the chelating agent. In the former case, 35 the covalent bond is formed after removal of the hydrogen

- 10 -

from the hydroxyl groups of the support. The covalent bonding site on the support is designated herein as "SUPPORT-O-". In one embodiment of the present invention, the composite material useful for removing heavy metals from waste streams has formula (I) below:



wherein at least one of R_1 - R_3 are SUPPORT-O- and the other of R_1 - R_3 are the same or different and are unsubstituted or halosubstituted alkyl groups having 1-5 carbon atoms and R_4 is



a is an integer of 1-20, b is an integer of 2-8, c is an integer of 0-5 and d is an integer of 1-5. Particularly preferred thiol-containing composites are obtained when R_1 - R_3 are each SUPPORT-O- and R_4 is either $(\text{CH}_2)_3$ -SH or $(\text{CH}_2)_3$ -O- $\text{CH}_2\text{CHSHCH}_2\text{SH}$.

In accordance with the present invention, the thiol-containing composite described by formula (I) above is produced by covalent attachment of the thiol group of a thiol-containing silane coupling agent on the surface of an inorganic carrier. Covalent attachment can be accomplished, for example, by refluxing a solution of the thiol-containing silane with the inorganic carrier under heat for about 16-20 hours. A preferred synthesis includes first suspending

- 11 -

about 20.0 g of 70-270 mesh silica gel in a thiol-containing-silane in solvent (e.g., toluene) solution having a concentration of about 50 volume percent ("v/v%"). The silane mixture is refluxed at about 75°C for a time
5 sufficient to effect covalent bonding of the thiol (e.g., about 15-20 hours). Example 1 below further illustrates an exemplary synthesis of inventive compositions according to Formula I.

Exemplary thiol-containing silanes include
10 mercaptoalkylsilanes (e.g., (3-mercaptopropyl)triethoxy silane, and (3-mercaptopropyl)trimethoxy silane). Various solvents such as benzene, toluene, xylene, hexane, or cyclohexane can be used to prepare a solution of the mercaptoalkylsilane. A preferred mercaptoalkylsilane
15 solution is 10 to 50 volume percent (3-mercaptopropyl)triethoxy silane in toluene.


The thiol-containing composite materials of the present invention can be used to remove a variety of heavy metals from waste streams including, for example, cadmium,
20 lead and zinc. The thiol-containing composites are particularly selective for cadmium and are able to remove cadmium from waste streams. With regard to lead, the thiol-containing composites will remove lead most effectively at pHs greater than 5.0, preferably greater than 6.5. In
25 addition, the thiol-containing composites can remove copper selectively from waste streams containing, for example, copper and nickel. Consequently, the thiol composites of the present invention are particularly effective in treating waste streams containing low concentrations of cadmium
30 (i.e., anywhere from 1.0 to 200 parts per million ("ppm")) as well as waste streams containing higher concentrations. If the waste stream is to be buffered to attain and/or maintain optimum operating pHs, any conventional buffering system (e.g., acetic acid/ammonium hydroxide, potassium hydrogen
35 phthalate/sodium hydroxide, tris(hydroxymethyl)aminomethane/

- 12 -

hydrochloric acid) can be utilized. Likewise, pH adjusting agents (e.g., ammonium hydroxide, hydrochloric acid) can be used to adjust the fluid stream pH.


In another embodiment, a chelating composition is prepared by covalent attachment of both a thio and an amino group on the surface of an inorganic carrier. Chemically active ceramic compounds having both a thio and amino group on the surface of an inorganic carrier have the following formulae:

10



15

and



20 wherein

at least one of R_{41} - R_{43} and one of R_{41}' - R_{43}' are SUPPORT-O-

R_{44} is $-(\text{CH}_2)_a\{\text{S}-(\text{CH}_2)_b\}_c\text{SH}$, wherein a is an integer from 1-20, b is an integer from 2-8 and c is an integer from 25 0-5.

R_{44}' is an amine; and other of R_{41} - R_{43} and R_{41}' - R_{43}' are the same or different and are unsubstituted or halo-substituted alkyl groups having 1-5 carbon atoms, R_{44} or R_{44}' .

30

For example, a mixture of one mercaptoalkylsilane (e.g., 3-mercaptopropyl-triethoxy silane, 3-mercaptopropyl-trimethoxy silane, etc.) and one aminoalkyl silane (e.g., 3-aminopropyl-triethoxy silane, 3-aminopropyltrimethoxy silane, etc.) can be prepared in equimolar concentration in 35 suitable solvents (e.g., benzene, toluene, xylene, hexane,

- 13 -

cyclohexane) to have equal surface coverage of both thio and amino groups on the surface of the support or in different ratios to vary the surface coverage of the thiol and amino groups on the support. The relative ratio of the thiol and amino groups on the inorganic carrier can be used to control the selectivity of the individual composition.


It has been discovered that amine-containing compounds as disclosed in the present invention are particularly selective for copper ions in waste streams. Accordingly, the thiol/amine composite materials can be prepared in such a way to maximize removal of heavy metals according to the concentration of heavy metals contained in a given waste stream. Although ligands containing either nitrogen or sulfur can form strong complexes with heavy metal ions, they do not seem to have good selectivity. For example, if a waste stream contained relatively large amounts of copper and small amounts of cadmium, a composite material containing a relatively large amount of amine and relatively smaller amounts of thiol could be prepared by modifying the molar quantities of the precursor materials used in preparing the composites. The optimum operating pH for the thiol/amine composites will depend on the relative ratios of amine and thiol on the material. Generally, the thiol/amine composites should be used in liquid streams having a pH in the range of about 2 to 10.

One advantage of the thiol and thiol/amine composites of the present invention is that, once saturated, the composite material can be quickly, easily and inexpensively regenerated (i.e., stripped of accumulated heavy metal ions). Simple regeneration of the materials provides three important advantages: (1) it facilitates reuse of the composite material, (2) avoids creation of voluminous amounts of heavy metal laden sludge that must be buried or otherwise stored, and (3) allows recapture of the excess heavy metal for recycling back into the original

manufacturing process. Regeneration of the thiol composites can be accomplished by treating the materials with dilute mineral acids (e.g., hydrochloric acid, nitric acid, sulfuric acid, perchloric acid, acetic acid, formic acid).

5 A preferred method of regenerating the thio composite materials is by contacting the material with approximately 0.05 M hydrochloric acid.


In another embodiment of the present invention, composite materials useful for removing heavy metals from
 10 waste streams are produced using amine salts as chelating agents. Amine salt-containing composites according to the present invention have formula (II) below:



wherein

1) at least one of R_9 , R_{10} or R_{11} is SUPPORT-O- and R_{12} is

20




25 wherein:

a) R_{13} is


i) an unsubstituted or lower aryl or lower alkyl substituted saturated hydrocarbon chain having 1-20 carbon atoms,

30




wherein R₁₇-R₂₀ are the same or different and are -H or -(CH₂)_fCH₃, where f is an integer from 0-20 and e is an integer from 1-5, or

5




wherein R₂₁ is -(CH₂)_mCH₃,



10 and g is 1-10, h is 1-10, j is 1-20, k is 1-5, m is 0-10 and X⁻ is a chlorine, bromine or iodine atom ion;

b) two or three of R₁₄, R₁₅ and R₁₆ are -(CH₂)_mCH₃,

15



and other of R₁₄, R₁₅ and R₁₆ are H; and

2) other of R₉, R₁₀ and R₁₁ are R₁₂ or unsubstituted or halo-substituted alkyl groups having from 1 to 5 carbon atoms.

- 16 -

Preferred amine-salt containing composites generically described by the above formulae include propyl-tributylammonium chloride, propyl-trimethylammonium chloride, propyl-triethylammonium chloride, propyl-
5 dibutylammonium hydrogen chloride attached to a silica gel support.

The amine salt composites of the present invention are produced by covalent attachment of a quaternary ammonium or tertiary ammonium functional group via several routes.

10 One such route, for example, requires reacting inorganic carrier with a quaternary ammonium organofunctional silane (e.g., (triethoxy)silylpropyl trimethylammonium chloride, (trimethoxy)silylpropyl trimethylammonium chloride).

Another route of covalently attaching the quaternary or
15 tertiary ammonium compound is by reacting inorganic carrier with a silane (e.g., 3-chloropropyl-trimethoxy silane, 3-chloropropyl-triethoxy silane). Next, the modified inorganic carrier is reacted with a di- or tri- alkylamine (e.g., triethylamine, tripropylamine, tributylamine,
20 dibutylamine, dipropylamine, chloromethyl pyridine) to produce a tertiary or quaternary ammonium functional group on the modified inorganic carrier of different carbon chain length, size and hydrophobicity depending on the selection of the appropriate reagents. For example, a tertiary or
25 quaternary ammonium functional group can be prepared by varying the carbon chain length attached to the nitrogen atom in the respective functional group by reacting, for example, a chloro-alkyl modified inorganic carrier with trialkyl or dialkylamine. That type of amine salt, with
30 larger carbon chain length, will have a larger cation which has the tendency to form ion pairs with larger anionic heavy metal ions or anionic complexes of heavy metal ions (e.g., HCrO_4^- , HMoO_4^- , SbCl_6^-). On the other hand, amine salts with smaller carbon chain lengths will have a tendency to form
35 ion pairs with other smaller size anionic complexes of heavy

- 17 -

metal ions (e.g., CdCl_3^- , CdCl_4^{2-} , $\text{Zn}(\text{CN})_4^{2-}$, $\text{Cu}(\text{CN})_2^-$). The specificity of tertiary or quaternary ammonium functional groups is dependent on the charge to size ratio of heavy metal ions. Also, tertiary or quaternary ammonium functional composites can be prepared by varying the number of nitrogen atoms within a given carbon chain length (for example, triethylene tetramine, diethylene triamine) to facilitate multiple charges on one chain. These types of amine salts are specific for removal of highly charged ions (e.g., $\text{Cr}_2\text{O}_7^{2-}$, TcO_4^- , PbCl_4^{2-} , $\text{Fe}(\text{CN})_6^{4-}$, $\text{Fe}(\text{CN})_6^{3-}$).

The amine salt composites of the present invention can be used at a variety of pHs but have an optimum operating pH in the range of about 2 to 8. The amine salt composites can be used to selectively remove heavy metal ions such as lead, zinc, cadmium, copper, palladium, platinum, chromium(VI), molybdenum(VI), antimony(V).

Alternatively, composites according to the present invention can be produced by first coating an inorganic carrier with a titanium-containing compound (e.g., titanium(IV) chloride, titanium(IV) ethoxide, or titanium(IV) propoxide). In a preferred embodiment, inorganic carrier is titanized by reacting it with an approximately 20 volume percent solution of titanium(IV) chloride in, for example, dry hexane. The reaction is carried out under mild heating for 4 to 6 hours.

It has been unexpectedly discovered that the titanized inorganic carrier can then be used directly (i.e., without a group linking the chelating agent to the substrate) as a substrate for an amine or amine salt as a chelating agent. If an amine is to be attached to the titanized substrate, the titanized inorganic carrier is then further reacted with an amine by stirring the mixture in a vessel with a refluxing condenser to chemically immobilize the amine. Immobilization of the amine is, essentially, affixing the chelation molecule to the titanized silica


- 18 -

surface either by physical or chemical linkage. Chemical linkage can involve covalent attachment through carbon-carbon, carbon-nitrogen, or carbon-sulfur bonds, for example, to the titanized surface of the substrate.

5 Physical linkage involves intermolecular forces such as van der Waals', or dipole-dipole interactions. Exemplary amines include 1,4-diaminobutane, ethylene diamine, n-ethylethylene diamine or n-butylamine. Most preferably, n-butylamine can be used to produce butylamine immobilized titanized
10 inorganic carrier. Exemplary amine salts include the amine salts described above.

If an amine salt is to be attached to the titanized substrate, a covalent attachment mechanism such as the one described above relative to non-titanized substrates
15 can be used.

Composite materials prepared on titanized substrates and including an amine as a chelating agent according to the present invention have formula (III):




wherein one or both of R_7 and R_8 is SUPPORT-O- and other of
25 R_5 , R_6 , R_7 and R_8 are the same or different and are selected from the group consisting of monoamines or polyamines, wherein a nitrogen is bonded to said Ti atom. Preferably, the R groups that do not constitute the support and oxygen linkage each are polyamines having the formula $-NH-[(CH_2)_{aa}-$
30 $NH]_{bb}-(CH_2)_{aa}-NH_2$, wherein aa is an integer from 1-10 and bb is an integer from 0-20. Most preferably, two of R_5 , R_6 , R_7 and R_8 constitute the support and oxygen linkage and the remaining R groups are each a polyamine having the formula $-NH-[(CH_2)_{aa}-NH]_{bb}-(CH_2)_{aa}-NH_2$. In particularly preferred

embodiments, the polyamines attached to the remaining R groups are the same.

Monoamines and polyamines useful in preparing composite materials according to the present invention include butylamine, pentylamine, hexylamine, butylene diamine, triethylene tetraamine and pentaethylene hexaamine.

Composites prepared using titanized substrates and amine salts as chelating agents according to the present invention have formula (IV):


10



wherein:


15

1) one or both of R_{24} and R_{25} is SUPPORT-O- and other of R_{22} , R_{23} , R_{24} and R_{25} are the same or different and are




20


i) R_{26} is
 a) an unsubstituted or lower aryl or lower alkyl substituted saturated hydrocarbon chain having 1-20 carbon atoms, or




wherein v is 0-5 and w is 1-5 and R₃₀-R₃₃ are the same or different and are -H or -(CH₂)_dCH₃ wherein d is 0-20, or



5 wherein R₃₄ is




10




wherein p and q are the same or different and are 1-10, r is 1-20, t is 1-5 and X⁻ is a chlorine, iodine or bromine ion; and

15


ii) R₃₅ and two of R₂₇, R₂₈ and R₂₉ are




20



and other of R₂₇, R₂₈ and R₂₉ are H; or




wherein R₃₅ is as defined above and R₃₆ is
 i) an unsubstituted or lower alkyl or
 lower aryl substituted, saturated hydrocarbon chain having
 1-20 carbon atoms; or




wherein R₃₀-R₃₃ and R₃₇ are the same or different and are -H or
 $-(CH_2)_uCH_3$ wherein u is 0-20.

Preferred compositions of the compound described
 by Formula (IV) are:



15 or



The compositions of the present invention have the
 capability of removing, in a selective manner, heavy metal
 ions in dilute solutions from aqueous streams. The
 25 compositions of the present invention in general can be used
 for removal from aqueous streams heavy metals such as
 antimony, arsenic, beryllium, cadmium, chromium, copper,
 lead, mercury, nickel, selenium, silver, thallium, tin,

- 22 -

zinc, molybdenum, palladium, platinum, silver, gold, cobalt, technetium, rhenium and rare earth metals such as cerium, neodymium, and praseodymium.

Typically, the compositions of the present invention are placed in packed beds or fluidized beds and the waste stream is passed through the bed. The compositions act to chelate with the unwanted metal ions, even if the ions are present in only dilute concentrations. Examples of useful beds for the chelating compositions described herein are found in U.S. Patent Nos. 4,824,576 to Sood et al. and 4,448,694 to Plueddemann, the disclosures of which are hereby incorporated by reference.

The compositions of the present invention can be used for removal and recovery of heavy metal ions by a variety of methodologies as outlined by FIGS. 1 and 2. FIG. 1 is a process outline for separation and recovery of metal ions with chemically active inorganic carriers. FIG. 2 is a flow sheet illustrating the process of the invention by using a series of multiple adsorbent beds for metal ion separation and/or metal recovery.

The process of metal ion removal of the present invention contemplates several modes of operation. Many factors are considered in choosing the appropriate methodology, including the composition of the aqueous stream to be treated, the industrial process through which the contaminated aqueous stream is generated, the desired purification level of the aqueous stream, the degree of separation of metal ions from the waste stream desired, and the end use of the effluent from the bed.

In one embodiment of the present process, an operation mode can be employed to remove all metal ions simultaneously from an aqueous stream containing multiple metal ions by passing the stream through a single adsorbent packed bed or fluidized bed containing a composition according to the present invention. The column breakthrough

- 23 -

volume (i.e., volume at which a minimum threshold concentration of metal ions in the effluent is exceeded) can be determined by monitoring the metal ion concentration in the effluent with an atomic absorption spectrophotometer, flow injection analysis, ion selective electrodes, or other known methods of metal ion concentration analysis and/or monitoring pH of the effluent.

The loaded column (extent of column saturation when breakthrough volume occurred) can be regenerated by desorbing the adsorbed metal ions from the column. The adsorbed metal ions can be recovered simultaneously by, for example, stripping all metals from a bed of chemically active silica gel with mineral acid (e.g., nitric acid, hydrochloric acid), as discussed *supra*. Upon regeneration, the chemically active inorganic carrier bed can be used for the next operation. The metal ion concentrate obtained during regeneration can be used to recover metals present by any one of two techniques or the metals can be disposed of as a sludge as illustrated in FIG. 2. In the first recovery method, the metals are recovered by electrolysis. The second method involves recycling the metal concentrate back to the process which first generated the polluted aqueous stream. In the third method, the metals can be precipitated to form sludge which can subsequently be disposed of in an environmentally safe manner.

In accordance with the present invention, it has been unexpectedly discovered that the efficiency of the removal process relative to certain metal ions is dependent on the pH of the waste stream. Therefore, as shown in FIG. 2, the pH of the waste stream can be advantageously adjusted if necessary (depending on the composite material used). This process operation is typically performed by buffering an aqueous stream entering the bed of chemically active ceramic composition. Alternatively, instead of employing a buffer solution, it is possible to use a dilute ammonium

hydroxide solution to simply adjust the pH of an acidic aqueous stream entering the packed or fluidized bed of chemically active inorganic carrier. In that case, because the inventive materials are acidic in nature and release protons when they absorb metal ions, the pH of the effluent stream decreases as additional bed volumes pass through the bed. The pH of effluent stream decreases and reaches a minimum value whereby it becomes acidic. The inventive materials have a preferred pH band at which the adsorption efficiency for each metal ion is maximized. A pH below that pH is defined as acidic for the purposes of the present invention. At that pH, the adsorption of metal ions on the composite bed has been found to decrease. That point is termed the "breakthrough point" and can be determined by monitoring the pH of the effluent stream or by monitoring the metal ion concentration in the effluent aqueous stream.

At the breakthrough point, the flow of aqueous stream through the bed can be stopped, and the bed can be made operational again by passing one or more bed volumes (i.e., an amount of fluid equal to the volumetric fluid capacity of the bed) of buffer solution through the bed. Buffering the column reestablishes the initial pH and extends the adsorptive life of the column and allows its use for the adsorption of metal ions until the column approaches its adsorption capacity (i.e., the point at which substantially all of the available sites for chelation of heavy metal ions are occupied) as determined by the breakthrough volume.

Adjusting the fluid stream pH with ammonium hydroxide (rather than using a buffer at the start) is highly advantageous because it decreases the cost of operation and minimizes the contamination of the effluent aqueous streams with buffer solutions, enabling environmentally safe disposition of the effluent. It is

- 25 -

also possible to determine the breakthrough point by simply monitoring the pH of the effluent stream.

In another embodiment of the present process, all the metal ions in a waste stream containing more than one
5 type of species of metal ion can be simultaneously removed by passing the waste stream through the single bed of chemically active inorganic carriers.

The selectivity of the inventive materials is highly advantageous. For example, a single metal ion from
10 the aqueous stream containing multiple metal ions can be removed by passing the stream through a single packed or fluidized bed of the inventive composite materials where removal, recycling or disposal of only one metal ion is desired. The adsorbed metal ion can be desorbed from the
15 bed of chemically active inorganic carrier with mineral acid. For example, a composite material as described above can be used to remove cadmium from the aqueous stream buffered to a pH 6.5 and containing lead, calcium and magnesium. The adsorbed cadmium can be recovered by
20 stripping with dilute mineral acids, and the regenerated bed can be utilized for the next operation. The metal ion concentrate can be used to recover, recycle or dispose of lead using techniques such as electrolysis, recycling and precipitation, as discussed above.

25 The selectivity exhibited by certain of the compositions of the present invention is also highly advantageous due to the high concentration of metal ions such as calcium and magnesium present in typical waste streams that do not need to be removed. In conventional
30 heavy metal-removing beds, nonselective materials remove calcium or magnesium ions (as well as the heavy metal contaminants) and become quickly saturated due to the high concentration of magnesium and calcium in most aqueous waste streams. The bed must then be frequently regenerated (if
35 possible) or replaced. On the other hand, the inventive

- 26 -

composite materials selectively remove only the target heavy metal ions (e.g., lead, cadmium). Therefore, the composite material does not become as quickly saturated and can be used for longer periods without regeneration or replacement.

5 As noted more specifically in the Examples (*infra*) certain of the inventive materials (e.g., the thiol-containing composites) are capable of removing heavy metal ions for up to 250 (or more) bed volumes and have extraordinarily high adsorption capacities for cadmium.

10 In another embodiment of the process of the present invention, metal ions can be separately and specifically removed by adsorbing those metal ions on a series of metal ion selective beds. As illustrated in FIG. 2, the metal ions can be removed in a sequential manner from
15 the aqueous stream containing a mixture of multiple metal ions by passing the stream through the multiple beds where each bed contains an inventive composite that selectively removes one of the metal ions. The breakthrough point of the beds can be determined by monitoring the metal ion
20 concentration in the effluent stream from the column by the methods discussed *supra*. These multiple beds can then be regenerated as described above and the metal ions removed from the bed can be recycled or disposed of.

For example, copper can be removed from a waste
25 stream containing copper, lead, and/or cadmium by passing the stream first through a bed of amine-containing composites. The waste stream can then be conducted into a second bed containing thiol-containing composites to remove lead and/or cadmium. In that way the heavy metal ions are
30 separated from the waste stream and from each other and can be easily recaptured and recycled in to the original manufacturing process. Accordingly, the processes and materials of the present invention can completely remove and separate two distinct metal ions and facilitate maximum
35 utilization of the beds' relative capacities, thereby

- 27 -

providing valuable increased efficiency in the metal ion removal process.

The present invention is further described by the following non-limiting examples.

5

Example 1:

A 50 vol% solution of (3-mercaptopropyl)-trimethoxy silane in toluene was prepared. That solution was refluxed with silica gel beads 10 having a size of 70-270 mesh (surface area of about 500 m²/g and pore size 60 angstroms) at 70-80°C for 16 to 20 hours. The reacted silica gel was washed repeatedly with toluene and acetone and dried at 50-60°C. The material prepared according to this example is designated as Sample A.

15

Example 2:

A solution containing both γ -aminopropyltrimethoxy silane (29.8 vol%) and 3-mercaptopropyltrimethoxy silane (27.7 vol%) in toluene was prepared. That solution was 20 reacted with silica gel beads having a size of 70-270 mesh (surface area of about 500 m²/g and pore size 60 angstroms) by refluxing at 70-80°C for 10 to 12 hours. The reacted silica beads were filtered, washed with toluene, methanol and acetone and dried at 60-70°C. The composite beads 25 produced according to this example are designated as Sample B.

Example 3:

The surface of silica gel beads having a size of 30 70-270 mesh (surface area of about 500 m²/g and pore size 60 angstroms) was titanized by reacting silica gel with a 20 vol% solution of titanium(IV) chloride in dry hexane. The reaction was carried out at 70-75°C for 4 to 6 hours. The titanized silica gel was then reacted with n-butylamine by 35 placing the titanized silica gel beads in a 10 vol% solution

- 28 -

of n-butylamine in hexane at 65-70°C for 4 to 6 hours. The material prepared according to this example is designated as Sample C.

The extraction efficiency of Sample C composites
5 for copper and nickel was determined by equilibrating 25 ml of 200 ppm solution of copper and nickel at various pH with 1.0 g of Sample C. It was discovered that Sample C could adsorb copper quantitatively (more than 99.9%) at pH 9.0 while no adsorption of nickel was observed. Also, adsorbed
10 copper can be recovered by desorbing adsorbed copper with 0.1 M sulfuric acid.

Example 4:

A 25 vol% solution of (triethoxy)silylpropyltri-
15 methyl ammonium chloride (silylating agent) in toluene is prepared. Next, silica gel beads having a size of 70-270 mesh (surface area of about 500 m²/g and pore size 60 angstroms) were refluxed with the silylating agent solution in a 16.6 vol% mixture of toluene in ethanol. The reflux
20 reaction was allowed to proceed at 70°C for 12 hours. The refluxed silica gel beads were washed successively with toluene, ethanol, water and acetone, and dried at 40°C. The material prepared according to this example is designated as Sample D.

25

Example 5:

Sample A beads were packed in a one centimeter ("cm") diameter column to a height of 10 cm. Aqueous solution containing cadmium ions at a concentration of 200
30 parts per million ("ppm") were flowed throughout the packed column at a flow rate of 1 milliliter per minute to provide approximately 10 minutes of residence or contact time between the solution and the chemically active silica gels. The aqueous solution was buffered at pH 6.5 using acetate
35 buffer.

- 29 -

The capacity of the chemically active silica gel beads for a given metal ion was determined by performing breakthrough studies on the packed bed. Accordingly, an aqueous solution containing metal ions was passed through the column at a flow rate of 1 ml/minute and the metal ion concentration in the effluent from the column was determined with an atomic absorption spectrophotometer. Thus, capacity of the ceramic compositions was calculated from the total amount of metal ion absorbed on the bed at saturation of the bed.

The capacity of the packed column was determined according to the procedures described above. The concentration of the effluent was measured periodically to determine the number of bed volumes that could be treated by the packed column before the beads were saturated and no longer removed the metal ion from the stream. The initial capacity was calculated at the end of the first period of saturation of the bed. Saturation is defined as a state after which no more metal ions are adsorbed on the bed. Thus, after saturation of the bed the concentration of metal ion in the solution entering the bed (feed solution) is, generally, equal to the concentration of metal ions in the solution coming out of the bed (effluent solution). The packed bed saturated with metal ions was then regenerated by stripping the metal ions from the packed bed using 4 bed volumes of 0.05 molar hydrochloric acid at predetermined concentrations. The combined sequence of saturation of the bed with the metal ions from the feed solution and regeneration of the bed by stripping the adsorbed metal ion from the synthesized adsorbents in the bed is denoted as one cycle of operation.

The fresh capacity of the Sample A beads (i.e., the capacity after one cycle of operation) for cadmium was 80.36 mg/g. After 20 cycles, the capacity of the Sample A beads for cadmium was still an excellent 54.28 mg/g.

- 30 -

FIG. 3 illustrates the relationship between the ratio of metal ion concentration in the effluent stream to the metal ion concentration in the feed stream versus the bed volumes passed through the column. As shown by FIG. 3, the packed column containing material of the present invention was able to reduce the concentration of cadmium to less than 1 ppm up to approximately 250 bed volumes. The large number of bed volumes successfully treated by the packed column of Sample A beads illustrates the excellent capacity of the materials of the present invention. The large number of cycles after which a high capacity still remains illustrates the excellent durability of the materials of the present invention.

As shown in FIG. 4, the packed column was fully regenerated by washing the column with about 4 bed volumes of 0.05 M hydrochloric acid. Upon regeneration, 98.7 weight percent of the original cadmium that was removed from the waste stream which passed through the bed was recovered from the saturated beads.

Example 6:

Example 5 was repeated except that the fluid stream contained 54.5 ppm zinc, 50.5 ppm lead, and 50.5 ppm cadmium. FIG. 5 shows the relationship of the ratio of the respective zinc, cadmium and lead ion concentrations in an effluent stream to the respective zinc, cadmium and lead ion concentrations in a feed stream versus the bed volumes passed through the column of Sample A beads. As shown by FIG. 5, the packed column of Example 6 was able to reduce the concentration of cadmium, zinc and lead for up to 250 bed volumes to less than 1 ppm. Also FIG. 5 illustrates that cadmium would be removed from the bed for an additional 330 bed volumes. However, the additional removal of cadmium results in the desorption of zinc and lead from the bed. Therefore, this example indicates that Sample A beads are


- 31 -

more selective toward cadmium than to zinc or lead. That characteristic of the Sample A material is advantageous if it is desired to remove only cadmium from a solution containing for example, cadmium, zinc and lead.

5 Although the present invention has been described in detail for the purpose of illustration, it is understood that such detail is solely for that purpose, and variations can be made therein by those skilled in the art without departing from the spirit and scope of the invention as
10 described by the following claims.



WHAT IS CLAIMED IS:

1. A composite material suitable for removing heavy metal ions from waste streams, having the formula



wherein at least one of R_1 - R_3 is SUPPORT-O- and other of R_1 - R_3 are the same or different and are unsubstituted or halosubstituted alkyl groups having 1-5 carbon atoms and R_4 is

10



wherein

a is an integer from 1-20, b is an integer from 2-8, c is an integer from 0-5, and d is an integer from 1-5.

25 2. A composite material according to Claim 1, wherein only one of R_1 , R_2 , R_3 , is SUPPORT-O-.


30 3. A composite material according to Claim 2, wherein R_4 is $-(\text{CH}_2)_a\text{-SH}$ or $-(\text{CH}_2)_a\text{-O-CH}_2\text{-CHSH-CH}_2\text{SH}$.

4. A composite material according to Claim 1, wherein R_1 , R_2 and R_3 are SUPPORT-O- and R_4 is $-(\text{CH}_2)_3\text{-SH}$.

5. A method of removing heavy metal ions from a liquid stream comprising the step of contacting the stream



35

with a composite material under conditions effective to complex said heavy metal ions on said composite material, said composite material having the formula



wherein at least one of R_1 - R_3 is SUPPORT-O- and other of R_1 - R_3 are the same or different and are unsubstituted or halosubstituted alkyl groups having 1-5 carbon atoms and R_4 is

10



wherein

a is an integer from 1-20, b is an integer from 2-8, c is an integer from 0-5, and d is an integer from 1-5.

25 6. A method according to Claim 5, wherein only one of R_1 , R_2 and R_3 is SUPPORT-O-.

7. A method according to Claim 6, wherein R_4 is $-(CH_2)_a-SH$ or $-(CH_2)_d-O-CH_2-CHSHCH_2SH$.

30 8. A method according to Claim 5, wherein R_1 , R_2 and R_3 are SUPPORT-O- and R_4 is $-(CH_2)_3-SH$.

9. A method according to Claim 8, wherein said stream has a pH no less than about 3.5.

35

- 34 -

10. A method according to Claim 8, wherein said stream has a pH no less than about 6.5.

11. A method according to Claim 8, further
5 comprising the step of adjusting the pH of said stream to a value above 6.5 before said contacting.

12. A method according to Claim 5, further
10 comprising removing complexed metal ions from said composite material to regenerate said composite material.

13. A method according to Claim 5, wherein said contacting step comprises flowing said stream through a single packed or fluidized bed containing said composite
15 material for removal of a selected metal ion or metal ions from said stream containing multiple metal ions, separating a selected metal ion or metal ions from a plurality of other ions including Ca(II) and Mg(II).

20 14. A method according to Claim 13 in which the selected metal ion is Cd(II).

15 15. A method according to Claim 13 in which the selected metal ion is Pb(II).

25 16. A method according to Claim 13 in which the selected metal ion is Zn(II).

30 17. A method according to Claim 13 in which the selected metal ion is Cu(II).

18. A method according to Claim 13 in which the selected metal ion is Ag(I).

- 35 -

19. A method according to Claim 13 in which the selected metal ion is Hg(II).

20. A method according to Claim 13 in which the
5 selected metal ion is Pd(II).

21. A method according to Claim 13 in which the selected metal ion is Pt(II).

10 22. A method according to Claim 13 in which the selected metal ion is As(III).

23. A method according to Claim 13 in which the selected metal ions are Sn(II), Sn(IV), or mixtures thereof.
15

24. A method according to Claim 13 in which the selected metal ions are Au(I), Au(III), or mixtures thereof.

25. A method according to Claim 5, wherein said
20 contacting step comprises flowing said waste stream through a first packed bed containing said composite material and then through a second packed bed containing said composite material, wherein said first packed bed and said second packed bed are arranged in series.

25 26. A method according to Claim 25, wherein said first and said second packed bed contain different composite materials exhibiting different metal ion removal preferences.

30 27. A method according to Claim 25, wherein the pH of said stream is adjusted after leaving said first packed bed and before entering said second packed bed.

- 36 -

28. A method of making a composite material suitable for removing heavy metal ions from fluid waste streams comprising the steps of

providing an inorganic substrate having

5 terminal hydroxyl groups;

providing a thiol-containing silane compound;

and

covalently attaching said thiol-containing silane compound to the oxygen of said terminal hydroxyl

10 group.

29. A method according to Claim 28, wherein said thiol-containing silane compound is selected from the group consisting of mercaptoalkylsilanes and mercaptoarylsilanes.

15

30. A method according to Claim 29, wherein said thiol containing silane is 3-mercaptopropyl-trimethoxy silane.

20 31. A composite material suitable for removing heavy metal ions from waste streams, which material contains the compounds of the following formulae:



and



35 wherein

- 37 -

at least one of R_{41} - R_{43} and one of R_{41} '- R_{43} ' are SUPPORT-O-;

R_{44} is $-(CH_2)_a-[S-(CH_2)_b-]_cSH$, wherein a is an integer from 1-20, b is an integer from 2-8 and c is an integer from 0-5.

R_{44} ' is an amine; and

other of R_{41} - R_{43} and R_{41} '- R_{43} ' are the same or different and are unsubstituted or halosubstituted alkyl groups having 1-5 carbon atoms, R_{44} or R_{44} '.

10

32. The composite material of Claim 31, wherein said amine is selected from the group consisting of 1,4-diaminobutane, ethylene diamine, n-ethylethylene diamine, triethylene tetramine, n-butylamine, propyl amine, and tetraethylene pentamine.


15

33. The composite material according to Claim 31, wherein said R_{41} , R_{42} and R_{43} are SUPPORT-O- and R_{44} is $-(CH_2)_3-SH$, and R_{41} '', R_{42} ' and R_{43} ' are SUPPORT-O-, and R_{44} ' is $-(CH_2)_3-NH_2$.

20

34. A method of removing heavy metal ions from a liquid stream comprising the step of contacting the stream with a composite material under conditions effective to complex said heavy metal ions on said composite material, said composite material containing the compounds of the following formulae:


30



and

35

- 38 -



5 wherein

at least one of R_{41} - R_{43} and one of R_{41} '- R_{43} ' are SUPPORT-O-;

R_{44} is $-(CH_2)_a-[S-(CH_2)_b-]_cSH$, wherein a is an integer from 1-20, b is an integer from 2-8 and c is an integer from 0-5.

R_{44} ' is an amine; and

other of R_{41} - R_{43} and R_{41} '- R_{43} ' are the same or different and are unsubstituted or halosubstituted alkyl groups having 1-5 carbon atoms, R_{44} or R_{44} '.

15

35. A method according to Claim 34, wherein said R_{41} , R_{42} and R_{43} are SUPPORT-O-; R_{44} is $-(CH_2)_3-SH$; R_{41} '', R_{42} ' and R_{43} ' are SUPPORT-O-; and R_{44} ' is $-(CH_2)_3-NH_2$.

20

36. A method according to Claim 34, wherein said contacting step comprises flowing said stream through a single packed or fluidized bed containing said composite material for removal of a selected metal ion or metal ions from streams containing multiple metal ions.

25

37. A method according to Claim 34 in which the selected metal ion or metal ions present in said stream are Cu(II), Pb(II), Cd(II), Hg(II), Ag(I), Au(I), Au(III), Pd(II) or Pt(II) alone or in combination.


30

38. A method according to Claim 34, wherein said amine is selected from the group consisting of 1,4-diaminobutane, ethylene diamine, n-ethylethylene diamine, triethylene tetramine, n-butylamine, propyl amine, and tetraethylene pentamine.

35

- 39 -

39. A composite material suitable for removing heavy metals from waste streams said material having the formula:




10 one or both of R_7 and R_8 is SUPPORT-O- and other of R_5 , R_6 , R_7 and R_8 are the same or different and are selected from the group consisting of monoamines and polyamines, wherein a nitrogen is bonded to said Ti atom.

40. A composite material according to claim 39, 15 wherein said other of R_5 , R_6 , R_7 and R_8 are each a polyamine having the formula $-\text{NH}-[(\text{CH}_2)_{aa}-\text{NH}]_{bb}-\text{NH}_2$, wherein aa is an integer from 1-10 and bb is an integer from 0-20.

41. A composite material according to claim 40, 20 wherein two of R_5 , R_6 , R_7 and R_8 are SUPPORT-O- and two of R_5 , R_6 , R_7 and R_8 are the same.

42. A method of removing heavy metal ions from a liquid stream comprising the step of contacting the stream 25 with a composite material under conditions effective to complex said heavy metal ions on said composite material, said composite material having the formula:



35 one or both of R_7 and R_8 is SUPPORT-O- and R_5 , and R_6 , and other of R_7 and R_8 are the same or different and are selected from the group consisting of

- 40 -

monoamines and polyamines, wherein a nitrogen is bonded to said Ti atom.


43. A method according to Claim 42, wherein said
5 contacting step comprises flowing said stream through a single packed or fluidized bed containing said composite material for removal of selected metal ion or ions from said stream containing multiple metal ions.

10 44. A method set forth in Claim 43 in which the selected metal ion is Cu(II).

45. A method of making a composite material suitable for removing heavy metal ions from fluid waste
15 streams comprising the steps of:
providing an inorganic substrate having a terminal hydroxy group;
covalently attaching a titanizing agent to the oxygen of said terminal hydroxy group; and
20 covalently attaching an amine to titanium atoms of said titanizing agent.


46. A method according to Claim 45, wherein said titanizing agent is titanium(IV) chloride and said amine is
25 n-butylamine.

47. A composite material suitable for removing heavy metals from waste streams having the formula:



wherein

1) at least one of R_9 , R_{10} or R_{11} is SUPPORT-O-
35 and R_{12} is




5

wherein:


a) R_{13} is

i) an unsubstituted or lower aryl or lower alkyl substituted saturated hydrocarbon chain having 10 1-20 carbon atoms,




wherein R_{17} - R_{20} are the same or different and are -H or $-(\text{CH}_2)_f\text{CH}_3$, where f is an integer from 0-20 and e is an integer from 1-5, or

15



wherein R_{21} is $(\text{CH}_2)_m\text{CH}_3$,



20


- 42 -

and g is 1-10, h is 1-10, j is 1-20, k is 1-5, m is 0-10,
and X⁻ is a chlorine, bromine or iodine ion;

b) two or three of R₁₄, R₁₅ and R₁₆ are

-(CH₂)_mCH₃,

5




and other of R₁₄, R₁₅ and R₁₆ are H; and

2) other of R₉, R₁₀ and R₁₁ are R₁₂ or

10 unsubstituted or halo-substituted alkyl groups having from
15 1-5 carbon atoms.

48. A composite material according to Claim 47,
wherein R₉, R₁₀ and R₁₁ are SUPPORT-O-, R₁₃ is -(CH₂)₃ and R₁₄,
15 R₁₅ and R₁₆ are -CH₃.

49. A method of removing heavy metal ions from a
liquid stream comprising the step of contacting the stream
with a composite material under conditions effective to
20 complex said heavy metal ions on said composite material,
said composite material having the formula:




25

wherein

1) at least one of R₉, R₁₀ or R₁₁ is SUPPORT-O-
and R₁₂ is

30




wherein


35

a) R₁₃ is

i) an unsubstituted or lower aryl or lower alkyl substituted saturated hydrocarbon chain having 1-20 carbon atoms,




5 wherein R₁₇-R₂₀ are the same or different and are -H or -(CH₂)_fCH₃, where f is an integer from 0-20 and e is an integer from 1-5, or



wherein R₂₁ is (CH₂)_mCH₃,


10



and g is 1-10, h is 1-10, j is 1-20, k is 1-5, m is 0-10 and X⁻ is a chlorine, bromine, or iodine ion;

15

b) two or three of R₁₄, R₁₅ and R₁₆ are -(CH₂)_mCH₃,



20

and other of R₁₄, R₁₅ and R₁₆ are H; and

- 44 -

2) other of R_9 , R_{10} and R_{11} are R_{12} , or unsubstituted or halo-substituted alkyl groups having 1 to 5 carbon atoms.

5 50. A method according to Claim 49, wherein said contacting step comprises flowing said stream through a single packed or fluidized bed containing said composite material for removal of selected metal ion or ions from said stream containing multiple metal ions, separating a selected
10 metal ion or metal ions from a plurality of other ions including Ca(II) and Mg(II).

 51. A method set forth in Claim 50 in which the selected metal ions are anionic oxyanions of metal ions and
15 anionic complexes of metal ions.

 52. A method according to Claim 51, wherein the selected anionic oxyanion is CrO_4^{2-} , MoO_4^{2-} , or TcO_4^- alone or in
20 combination.

 53. A method according to Claim 51, wherein the selected anionic complex is SbCl_6^- , AuCl_4^- or $\text{UO}_2\text{Cl}_4^{2-}$ alone or
in combination.

25 54. A method of making a composite material suitable for removing heavy metal ion from fluid waste streams comprising the steps or:

 providing an inorganic substrate having terminal hydroxyl groups;


30 providing a quaternary amine containing silane compound; and

 covalently attaching said quaternary amine containing silane compound to the oxygen of said terminal hydroxyl group.

35

55. A method according to Claim 54, wherein said quaternary amine containing silane compound is triethoxy-silyl-propyltrimethyl ammonium chloride.

5 56. A composite material suitable for removing heavy metals from waste streams having the formula:




10

wherein

1) one or both of R_{24} and R_{25} is SUPPORT-O- and other of R_{22} , R_{23} , R_{24} and R_{25} are the same or different and are


15




wherein

i) R_{26} is


a) an unsubstituted or lower aryl or lower alkyl substituted saturated hydrocarbon chain
 20 having 1-20 carbon atoms, or




wherein v is an integer from 0-5, w is an integer from 1-5, R₃₀-R₃₃ are the same or different and are -H or -(CH₂)_dCH₃ wherein d is an integer from 0-20 or



5 wherein R₃₄ is




10




wherein p and q are the same or different and each is an integer from 1-10, r is an integer from 1-20, t is an integer from 1-5 and X⁻ is a chlorine, bromine, or iodine ion; and


15 ii) R₃₅ and two of R₂₇, R₂₈ and R₂₉ are



20




and other of R₂₇, R₂₈ and R₂₉ are H; or



wherein R₃₅ is as defined above and R₃₆ is

i) an unsubstituted or lower alkyl or lower aryl substituted, saturated hydrocarbon chain having 1-20 carbon atoms; or


5



wherein R₃₀-R₃₃ and R₃₇ are the same or different and are -H or -(CH₂)_uCH₃, wherein u is an integer from 0-20.

57. A method of removing heavy metal ions from a liquid stream comprising the step of contacting the liquid stream with a composite material under conditions effective to complex said heavy metal ions on said composite material, said composite material having the formula:


15



wherein

1) one or both of R₂₄ and R₂₅ is SUPPORT-O- and other of R₂₂, R₂₃, R₂₄ and R₂₅ are the same or different and are

20




- 48 -

wherein



i) R_{26} is

- a) an unsubstituted or lower aryl or lower alkyl substituted saturated hydrocarbon chain having 1-20 carbon atoms, or




wherein v is an integer from 0-5, w is an integer from 1-5 and R_{30} - R_{33} are the same or different and are $-H$ or $-(CH_2)_dCH_3$ wherein d is an integer from 0-20, or

10


wherein R_{34} is

15





wherein p and q are the same or different and each is an integer from 1-10, r is an integer from 1-20, t is an integer from 1-5 and X is chlorine, bromine or iodine ion and


- 49 -

ii) R_{35} and two of R_{27} , R_{28} and R_{29} are

5

and other of R_{27} , R_{28} and R_{29} are H;10 wherein R_{35} is as defined above and R_{36} is

i) an unsubstituted or lower alkyl or lower aryl substituted, saturated hydrocarbon chain having 1-20 carbon atoms; or



15 wherein R_{30} - R_{33} and R_{37} are the same or different and are -H or $-(CH_2)_uCH_3$ wherein u is an integer from 0-20.

58. A method of making a composite material suitable for removing heavy metal ions from fluid waste streams comprising the steps of:

20

- 50 -

providing an inorganic substrate having a terminal hydroxy group;

covalently attaching a titanizing agent to the oxygen of said terminal hydroxy group;

5 covalently attaching an amine to titanium atoms of said titanizing agent; and

covalently attaching a halosubstituted hydrocarbon to a nitrogen atom of said amine.




FIGURE 1




FIGURE 2




FIGURE 3




FIGURE 4




FIGURE 5

INTERNATIONAL SEARCH REPORT

International application No.
PCT/US95/12327

A. CLASSIFICATION OF SUBJECT MATTER

IPC(6) :C02F 1/42; B01J 20/02, 20/10
US CL :210/688; 502/405, 407
According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
U.S. : 210/688; 502/405, 407

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US, A, 4,752,398 (HOLBEIN ET AL) 21 June 1988, col. 5, lines 5-45	31-38
A	US, A, 4,952,321 (BRADSHAW ET AL) 28 August 1990, col. 1, lines 7-46	1-38
A	US, A, 4,959,153 (BRADSHAW ET AL) 25 September 1990, col. 1, lines 9-68	1-30
X	US, A, 5,039,419 (BRADSHAW ET AL) 13 August 1991, col. 2, line 18 thru col. 3, line 7	1-30
A	US, A, 5,078,978 (TARBET ET AL) 7 January 1992, col. 2, line 33 thru col. 3, line 47	1-38


Further documents are listed in the continuation of Box C. See patent family annex.

* Special categories of cited documents:	*T	later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
*A		document defining the general state of the art which is not considered to be of particular relevance
*E		earlier document published on or after the international filing date
*L		document which may throw doubt on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
*O		document referring to an oral disclosure, use, exhibition or other means
*P		document published prior to the international filing date but later than the priority date claimed
	*X	document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
	*Y	document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
	*Z	document member of the same patent family

Date of the actual completion of the international search
19 JANUARY 1996

Date of mailing of the international search report
08 FEB 1996

Name and mailing address of the ISA/US
Commissioner of Patents and Trademarks
Box PCT
Washington, D.C. 20231

Authorized officer

SHARON GIBSON
Telephone No. (703) 308-3812

Facsimile No. (703) 305-3230

INTERNATIONAL SEARCH REPORT

International application No.

PCT/US95/12327

BOX II. OBSERVATIONS WHERE UNITY OF INVENTION WAS LACKING

This ISA found multiple inventions as follows:

This application contains the following inventions or groups of inventions which are not so linked as to form a single inventive concept under PCT Rule 13.1. In order for all inventions to be examined, the appropriate additional examination fees must be paid.

Group I, claim(s) 1-38, drawn to composite materials, method of using, and method of making containing thiol group covalently bonded to silica support.

Group II, claim(s) 39-46 and 56-58, drawn to composite materials, method of using, and method of making containing amine group covalently bonded to titania support.

Group III, claim(s) 47-55, drawn to composite materials, method of using, and method of making containing amine-salt group covalently bonded to silica support.

The inventions listed as Groups I, II, and III do not relate to a single inventive concept under PCT Rule 13.1 because, under PCT Rule 13.2, they lack the same or corresponding special technical features for the following reasons: Groups I and III contain silica support but with different ligands being covalently bonded thereon. Thiol ligand is covalently bonded to silica support in Group I whereas amine-salt ligand is covalently bonded to silica support in Group III.

Group II contains titania support whereas Groups I and III contain silica support.

INTERNATIONAL SEARCH REPORT

International application No.
PCT/US95/12327

Box I Observations where certain claims were found unsearchable (Continuation of item 1 of first sheet)

This international report has not been established in respect of certain claims under Article 17(2)(a) for the following reasons:

1. Claims Nos.:
because they relate to subject matter not required to be searched by this Authority, namely:

2. Claims Nos.:
because they relate to parts of the international application that do not comply with the prescribed requirements to such an extent that no meaningful international search can be carried out, specifically:

3. Claims Nos.:
because they are dependent claims and are not drafted in accordance with the second and third sentences of Rule 6.4(a).

Box II Observations where unity of invention is lacking (Continuation of item 2 of first sheet)

This International Searching Authority found multiple inventions in this international application, as follows:

Please See Extra Sheet.

1. As all required additional search fees were timely paid by the applicant, this international search report covers all searchable claims.
2. As all searchable claims could be searched without effort justifying an additional fee, this Authority did not invite payment of any additional fee.
3. As only some of the required additional search fees were timely paid by the applicant, this international search report covers only those claims for which fees were paid, specifically claims Nos.:

4. No required additional search fees were timely paid by the applicant. Consequently, this international search report is restricted to the invention first mentioned in the claims; it is covered by claims Nos.:

1-38

Remark on Protest

- The additional search fees were accompanied by the applicant's protest.
 No protest accompanied the payment of additional search fees.